


Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client : National Flo 13 Dulwich Loganholme			Test Numb Issue Date Print Date	er: :	16-00340 20/07/20 9/08/2016	16
Sample Description	Clients Ref : "Illusion Vinyl Flooring Nominal Composition : Nominal Thickness :	Loose lay plank" Polyvinylchloride (PVC) 5mm				
S/ISO 9239.1-2003	Reaction to Fire Tests for Radiant Heat Source	or Floorings. Determinati	on of the Burning E	Behavi	iour using a	
	Date of Sample Arrival		28/06/2016			
	Date Tested 20/07/2016					
	CHF Value	1	2	3	Mean	
	Length	7.2	8.3	8.5	8.0	kW/m²
	Width	9.3	-	-	-	kW/m²
	Smoke Value	1	2	3	Mean	
	Length	239	198	207	215	%.min
	Width	122	-	-	-	%.min
	Blistering				Yes	
	The test results relate to	the behaviour of the test s y are not intended to be s			der the partic	

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.



APPROVED SIGNATORY

MANAGING DIRECTOR

(C)